

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 02-140272

(43)Date of publication of application : 29.05.1990

(51)Int.Cl.

C09C 3/10
C08F 2/22
C08F214/00
C08F216/18
C08F218/08
C08F220/02
C08F220/10
C08F220/52
C08F226/06
C08F236/06
C09D201/00
D21H 19/38

(21)Application number : 63-294191

(71)Applicant : JAPAN SYNTHETIC RUBBER CO
LTD

(22)Date of filing : 21.11.1988




(72)Inventor : SAKURAI FUJIO
KAWAHASHI NOBUO
TADENUMA HIROSHI

(54) CROSSLINKED HOLLOW POLYMER PIGMENT AND COATING COMPOSITION USING THE PIGMENT

(57)Abstract:

PURPOSE: To provide the subject pigment composed of a hollow polymer particle having an inner layer consisting of a specified crosslinked polymer and an outer layer consisting of a non-crosslinked polymer, suitable for a coating material for paper, woodworking products, etc., and capable of providing a paper for paper coating excellent in whiteness, printability and balance.

CONSTITUTION: The subject hollow polymer particle pigment consisting of a crosslinked hollow polymer



particle having two or more polymer layers and having 0.15-20 μ m average particle diameter, 0.2-0.8 ratio of hollow diameter to particle diameter of the particle, \geq 85wt.% ratio of toluene-insoluble portion and <0.2 g/10min. melt flow rate at 180°C and 10kgf/cm² where the inner layer of the above-mentioned two polymer layers is consisting of a crosslinked polymer composed of (A) a polymerization unit of formula I (n is 2 or 3), (B) another polymerization unit of formula II (Y is phenyl, etc.) and (C) the other polymerization unit of formula III. And the outer layer of the above-mentioned particle is consisting of a crosslinked polymer composed of the component (A) as the essential component and the components (B) and (C) as necessary.